

# 15 MM PRIME - HERRINGBONE INVISIBLE A16545



D .				1
Dime	nsion	р	lan	k

LENGTH	23-2/3" (600 mm)
WIDTH	5-3/8" (135 mm)
TOTAL THICKNESS	5/8" (15 mm)

Dimension box	
BOX LENGTH	24" ( 610 mm)
BOX WIDTH	11" (280 mm)
BOX THICKNESS	7" (180 mm)
BOX WEIGHT	51 lb

LAYERS/BOX	24
SQFT/BOX	20.88 saft

### Dimension pallet

PALLET LENGTH	39-1/3" (1000 mm)
PALLET WIDTH	47-1/4" (1200 mm)
PALLET HEIGHT	41-1/3" (1050 mm)
PALLET WEIGHT	2090 lb
BOX/PALLET	40
SQFT/PALLET	837.00 saft

### **FEATURES**

Top layer

WOOD TYPE	Oak
LATIN NAME	Quercus Robur
GRADE	PRIME
CONSTRUCTION	2-layer
BEVEL	Micro bevel 4 sides (0.5 mm)
SURFACE STRUCTURE	Brushed

Composition of the support

SUPPORT TYPE	Engineered
BASE OF THE SUPPORT	Plywood

#### Placement

SYSTEM

Tongue and groove

#### APPLICATIONS

- · Light household use
- · Moderate commercial use
- · Normal commercial use
- · Normal household use
- · Intensive commercial use

#### UNDERFLOOR HEATING

Yes

RE-SANDABLE

Yes

<sup>©</sup> This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



# 15 MM PRIME - HERRINGBONE INVISIBLE A16545

## TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m² k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

## **CERTIFICATION**









